



## CORROSION INHIBITING VpCI® POWDERS

# VpCI®-609/609S Biodegradable Powders

## Corrosion Inhibiting Powder for Ferrous Metals Patent Pending



### PRODUCT DESCRIPTION

VpCI®-609 is a water-soluble Vapor phase Corrosion Inhibitor (VpCI®) powder for wet or dry corrosion protection of ferrous metals and aluminum. VpCI®-609 is also available as VpCI®-609S (with silica).

### FEATURES

- Accepted by Cefas as an offshore chemical. Registered under OCNS number 25717 allowing use at 5,000 ppm.
- Provides liquid, vapor-phase, and interface protection (above the liquid level).
- Creates a monomolecular inhibiting layer on metal surface.
- Provides up to 24 months of continuous protection.
- Does not contain nitrites, phosphates, or heavy metals.

### ADVANTAGES

- Vapor-phase inhibiting action protects inaccessible and recessed surfaces
- If the VpCI® layer is disturbed by moisture or the opening of an enclosed space, the layer is replenished by continuous vapor redeposition.
- Prevents future corrosion of pre-coated and painted surfaces.
- VpCI® layer typically does not need to be removed prior to processing or use.
- If required, powder is easily removed by air gun or water flush.
- Does not increase alkalinity.
- Provides economical protection for very large applications.

### TOXICOLOGICAL TESTING RESULTS

(Performed by Nortech A.S. (Norway))\*

- Biodegradability: 100% biodegradable in marine environment, rapidly degradable substance (OECD\*\* 306, BOD 28 Marine test).
- Toxicity: Very low (LD-50 = 5,000 mg oral-rat).
- Bioaccumulation potential: none (OECD Guideline 117).

\*Testing performed in accordance with Oslo-Paris commission protocol

\*\*Organization for Economic Co-Operation and Development

### TYPICAL USES

- Tubular structures, pipes, and vessels.
- Voids, cavities, and tanks.
- Internal surfaces of compressors, turbines, engines, tanks, boilers, heat exchangers.
- Steam condensate lines, closed circuit heating, and cooling systems
- Equipment during and after hydrostatic testing.
- Parts, components, and completed assemblies during shipping and storage.
- Additive to shot-blasting media, wet blasting.
- Additive to standing water.

### PHYSICAL PROPERTIES

#### VpCI®-609

Appearance	Off white crystalline powder
pH	6-7 (1% aqueous solution)
Solubility in water	15%
Bulk Density	38-39 lb/ft <sup>3</sup> (0.61-0.63 kg/l)

#### VpCI®-609S

Appearance	White to off white powder
pH	5.9-6.9 (1% water)
Bulk Density	37-38 lb/ft <sup>3</sup> (0.59-0.61 kg/l)

### METALS PROTECTED

- Carbon steel
- Stainless steel
- Aluminum
- Other ferrous metals

## METHOD OF APPLICATION

Apply VpCI®-609 in dry form by dusting, fogging, or sprinkling. Apply VpCI®-609 in aqueous form by spray, flush, or immersion. After application simply cover and close or seal the interior cavity or void (Fogging is easily achieved by using a low pressure air hose and sandblast cup. Large conventional sandblasting systems can also be used).

## DOSAGE

For powder application with average environmental conditions, use 0.3-0.5 ounce (8.5-14 grams) of VpCI®-609 per 1 cubic foot (28 liters) of enclosed space (300-500 g/m³). The dosage can be increased for more severe conditions. For aqueous submersion or partial submersion applications, consult your Cortec® Representative.

## METHOD OF REMOVAL

When required, VpCI®-609/609S in powder form can be easily removed by using a low pressure air gun or by a water rinse. Typically, if applied in aqueous form, the product does not require removal. If necessary, a simple water rinse or flush will suffice.

## PACKAGING AND STORAGE

VpCI®-609/609S powders are available in 5 pound (2.3 kg), 50 pound (23 kg), and 100 pound (45 kg) moisture barrier bags packed in fiber-lined drums. Also available in pouches such as EcoPouch®. Store in a sealed container in a dry warehouse and avoid direct exposure to sunlight with temperatures not exceeding 150°F (65°C). Under these conditions shelf life is up to 24 months.

**FOR INDUSTRIAL USE ONLY**  
**KEEP OUT OF REACH OF CHILDREN**  
**KEEP CONTAINER TIGHTLY CLOSED**  
**NOT FOR INTERNAL CONSUMPTION**  
**CONSULT SAFETY DATA SHEET FOR MORE INFORMATION**

## LIMITATIONS

- Do not use on copper, copper-based alloys, and other soft yellow metals. Compatibility with non-metallics should be evaluated.
- Caking of powder may occur when it is exposed to moisture and then dried. The likelihood of this is increased when powder is exposed to high heat and multiple wet/dry cycles. To avoid caking of powder do not over apply or unevenly disperse the dry powder. In aqueous applications make sure powder has been totally dissolved before using. Over extended periods of protection, this caking may require a more involved cleaning procedure. Contact Cortec® for further details.
- Powder is not soluble in hydrocarbon fluids. Rinse powder from vessels before adding hydrocarbon fluid.
- Powder should be removed from the area on each side of weld before welding, or other high temperature processing.

Note: Regular VpCI®-609 has a tendency to clump. For dry fogging application use VpCI®-609S (with silica) where acceptable.

## STANDARD TEST METHODS

NACE Standard TM0208-2008	Vapor Inhibiting Ability
NACE RP0487-2000	Selection of Rust Preventives
OECD 306, BOD-28	Marine Biodegradability Test
EPA/600/4-90/027F	Sea Water Toxicity Test
MIL-I-22110C	Vapor Inhibiting Ability

### LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE.

AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA  
Phone (651) 429-1100, Fax (651) 429-1122  
Toll Free (800) 4-CORTEC, E-mail [info@cortecvci.com](mailto:info@cortecvci.com)  
<http://www.cortecvci.com>

Printed on recycled paper 100% post consumer

Revised: 01/24/17. Supersedes: 01/06/16. ©Cortec Corporation 2002-2016 of Cortec Corporation.  
All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. 2016, ©Cortec Corp. ISO accreditation applies to Cortec's processes only.

Distributed by:

077-5240590 טלפון ,76150 רחובות 15096 ת.ד.  
[www.glimmer.co.il](http://www.glimmer.co.il) [office@glimmer.co.il](mailto:office@glimmer.co.il)

