

FINE LEVELLING MORTAR FOR USE IN DOMESTIC BUILDINGS

PRODUCT DESCRIPTION

CEMDURE FINE is a self-levelling screed formulated from High Alumina Cement. It is a pre blended dry powder, designed for use in domestic buildings. CEMDURE FINE can be applied both manually or with an automatic continuous mixing pump (without mortar hopper) after addition of water.

APPLICATIONS

CEMDURE FINE is designed for use as a fine smoothing of domestic floors before covering.

ADVANTAGES

- Remarkable smoothness
- Maximum adherence
- Fast curing
- Seamless
- Shrink-proof and tension free



TECHNICAL DATA

Water content 19%. 50% RH and temperature of 20°C during processing

Flexural Strength	5 N/mm ² after 28 days
Compressive Strength	20 N/mm ² after 28 days
Adhesion to subfloor	> 2 N/mm ²
VOC-value	free from ammonia and formaldehyde
Particle size	max. 1 mm
Free shrinkage	< 0,4‰ (measured at 50% RH)
pH-value	approx. 11,5
Flowability (Flow ring test SS 923519 (diam.50x23mm))	160 mm
Water stability	water stable(expansion under water < free shrinkage)
Material consumption	approx. 1,75 kg per mm thickness/m ²

PROCESSING DATA

Water admixture	19% (4,75 liter/25 kg bag)
Min. floor temperature	+6 °C
Dry powder density	approx. 1,5 g/cm ³
Wet density	> 2 g/cm ³
Open time	approx. 25 minutes depending on the temperature
Curing time	1 - 2 hours for foot traffic 24 hours for light traffic 1 week for full loading
Storage	6 months in dry conditions, max. 20°C and 50% RH

USER GUIDE

CEMDURE FINE can be applied at thickness between 0 and 10 mm in one operation. The material can be laid up to 15 mm in one operation. The semi-hardened material may be easily formed or cut allowing any necessary adjustments to be made.

Under normal conditions foot-step traffic onto the floor is possible after 1-2 hours and the final heavy loading after 1 week depending on local conditions.

SUBFLOOR

CEMDURE FINE should be laid on a well prepared subfloor.

PREPARATION OF THE SUBFLOOR

The surface to be treated must be hard, sound and free from surface contamination, all dust should be vacuumed from the surface.

Concrete laitance and old coatings should be removed mechanically e.g. by shot blasting, scabbling or scarifying. Concrete contaminated by oil or grease may require flame gunning and/or treatment with a proper degreaser.

Apply CEMPRIME AC on the subfloor.

MIXING

Only use clean potable water with a max. temperature of +20°C at a rate of 4,75 liter per 25 kg bag. The mixed material should be used within 25 minutes.

CLEANING

All tools and equipment should be cleaned promptly with water.

APPLICATION

Door threshold, stairs, drains and gullies should be isolated with foam barrier strips. Larger areas should be divided into bays in the case a mixing pump is used. Normal width of the bay is 8 -12 meters, depending on the pump capacity.

HEALTH AND SAFETY



Contains quartz and cement, cement moist is corrosive. Protect eyes and prevent prolonged skin contact, keep out of reach of children. CEMDURE FINE does not contain casein or other protein bearing additives that develop ammonia during the curing process. For further information refer to the safety data sheet of CEMDURE.

Transport: No classified product.

GENERAL

The general information provided in the present technical description, application guidelines and other recommendations, is based on research and experience. However, the client is obliged to determine himself whether the products are suitable for use. The characteristics given here are average values, obtained at 20°C and 50% RH, and were drawn up according to the current state of technology. As of publication, the present technical descriptions will replace all previous ones.

Please take into account different local conditions such as ventilation, floor temperature and humidity.

Do not process at temperatures below +5° C.

High humidity and low temperatures slow down the constriction and the curing.

Do not add other products!

Consult our web site www.cemart.eu to download the latest version of our technical data sheet.



Cemart NV, Maatheide 76E, B-3920 Lommel



EN 13813 CT-C20-F5 - Cementitious screed

Reaction to fire	NPD	Wear resistance	NPD
Release of corrosive substances	CT	Sound insulation	NPD
Water permeability	NPD	Sound absorption	NPD
Water vapour permeability	NPD	Thermal resistance	NPD
Compressive strength	C20	Chemical resistance	NPD
Flexural strength	F5		

NPD = No Performance determined

ניצוץ עשיה לתעשיה

077-5240590

office@glimmer.co.il

www.glimmer.co.il

